

# Hydroprint White Cling Film C060HWC



## Product Data

**Product type:** White Polyester Cling Film for Colour Laser, Screen and Thermal Transfer print processes

**Appearance:** White with semi-opaque release

**Surface finish:** Matt coating

## Physical characteristics:

		Typical Value	Test method
Front Face Thickness $\mu$		60	
Total Thickness $\mu$		158	Electronic micrometer
Total Weight (gsm)		216	Internal method
CIE Coordinates	L*	96	DCI Spectraflash ( D65 10' UV incl.)
	a*	4	
	b*	- 11	

## Compatibility:

### Most Colour/Mono Laser printers and modern Copiers.

- § When printing Polyesters by laser or copier methods, the thick paper or film settings and recommended feed trays should be used where available.
- § Refer to the printer manual for settings for film/heavyweight products.
- § The printable surface is also suitable for screen print, offset litho (using fully oxidising inks) and thermal transfer.

## Applications and characteristics

- § Matt white film to create point-of-sale displays and removable stickers.
- § After removal of release film (assisted by the back-slits on A4 and US Letter sizes only), the cling surface sticks to glass, gloss paint, metal or any smooth dry surface.
- § There is no adhesive residue and it can be repositioned easily.
- § If the cling adhesive gets dirty/dusty it can be cleaned with cold tap water and when allowed to dry, will be reusable.

**CAUTION:** Some laminates such as Formica may cause the cling surface to behave like a permanent adhesive after time.

Not recommended for exterior vehicle use.

Customers should make their own assessment regarding suitability.

**Recommended conditions for use:** 10°C - 30°C, 50% - 70% RH

**for storage:** 10°C - 30°C, 20% - 50% RH

**Material Handling, and Shelf Life:** 18 Months

**NOTICE** The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.