

Hydrosol Solvent Matt White Taklite C148SMWT



Product Data

Product type: Polyester film for solvent inkjet printing
Appearance: White
Surface finish: Matt printable coated front with a repositionable stick fast backing

Physical characteristics:

	Typical Value	Test method	
Front Face Thickness μ	148	Electronic micrometer	
Total Thickness μ	192	Electronic micrometer	
Total Weight (gsm)	200	Internal method	
Opacity	99.2%		
CIE Coordinates	L*	98	DCI Spectraflash (D65 10' UV incl.)
	a*	3	
	b*	- 12	

Compatibility:

All UVC and silkscreen printers
All 'Ecosol' printers, e.g.: Roland, Mimaki, HP, Mutoh
'Mild Solvent' printers, e.g.: Mutoh Spitfire
'Hard Solvent' printers require testing for specific inks
Please make your own assessment though, as solvent inks can vary widely. This is more dependent on ink manufacturer and type than it is on printing machine

Applications and characteristics

- Anti-reflective matt surface for optimum ink adhesion, scratch- and waterresistance
- Bright white front for optimum contrast
- Print-to-Go. No lamination necessary, even for outdoor use, if allowed to harden and not attacked
- **Unique suction-cling properties**
- Repeat stick and peel for glass, metal, enamel and gloss paint.
- No residue, even after long term sticking.
- Ideal for repositionable window displays

CAUTION:

- **Lacquers, Varnishes and Laminates**, such as Formica, may cause the cling surface to behave like a permanent adhesive after time. Customers should test and satisfy themselves as to the suitability of the product.
- Not recommended for exterior vehicle use.

Recommended conditions for use: 10'C - 30'C, 30% - 70% RH
for storage: 10'C - 30'C, 20% - 50% RH

Material Handling, and Shelf Life: 18 Months

NOTICE The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.

Copyright Sensitizers Group 2005

Kernow Coatings Limited +44(0)1326 373147 e-mail: kc@sensitisers.com