

Graphic Matt Lighblock Film F268CLSL



Product Data

Product type: Colour Inkjet Film

Appearance: White

Surface finish: Matt printable coating one side, antistatic grey lighblock reverse

Physical characteristics:

		Typical Value	Test method
Total Thickness μ		288	Electronic micrometer
Total Weight (gsm)		386	Internal method
Opacity		99.8%	Internal method
CIE Coordinates	L*	97	DCI Spectraflash (D65 10° UV incl.)
	a*	- 0.3	
	b*	- 4.7	

Compatibility:

	Large Format	
	Aqueous Dye Inks	Aqueous Pigment Inks
HP	*** (1)	***
CANON	***	***
EPSON	**	**
ENCAD	***	***

Applications and characteristics

- § Dimensionally stable polyester film base, with excellent light blocking properties and a robust feel.
- § Fast drying and smudge resistant, but not water resistant.
- § Suitable for dye and pigment inks using **less than 250%** saturation.
- § For multi panel POP-UP displays and applications requiring light blocking performance.

Caution: (1) It has been noted with Hewlett Packard 5000 series machines, using HP dye inks to print mixed colours containing less than 50% magenta, that the magenta fades quickly with light exposure causing a colour shift. Tests have, however, shown this also to be the case with most other synthetic materials. If this is a concern, you must satisfy yourself as to the suitability of this product for your application or switch to pigment-based (HP UV) inks, where light-stability is much better.

Lamination

'Over-lamination of this product after printing can be satisfactorily achieved, however, we strongly recommend that the user ensures the ink of the printed image is thoroughly dry before over-laminating. Printed areas with high ink loadings, which are not thoroughly dry, may cause de-lamination of the laminate. Where there is any doubt regarding the ink being dry we strongly recommend leaving the printed product to dry for a minimum of 24 hours before over-lamination takes place.'

Recommended conditions for use: 10°C - 30°C, 30% - 70% RH
for storage: 10°C - 30°C, 20% - 50% RH

Material Handling, and Shelf Life: 18 Months

NOTICE The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.