

# Ultra Matt Lightstop Film (White) F270CUSW



## Product Data

**Product type:** Colour Inkjet Film (polyester)

**Appearance:** White

**Surface finish:** Matt coating

## Physical characteristics:

		Typical Value	Test method
<b>Total Thickness <math>\mu</math></b>		320	Electronic micrometer
<b>Total Weight (gsm)</b>		398	Internal method
<b>Opacity</b>		100	Internal method
<b>CIE Coordinates</b>	<b>L*</b>	98	DCI Spectraflash ( D65 10° UV incl.)
	<b>a*</b>	1	
	<b>b*</b>	- 5	

## Compatibility:

	Large Format	
	Aqueous Dye Inks	Aqueous Pigment Inks
<b>HP</b>	***	***
<b>CANON</b>	***	***
<b>EPSON</b>	***	***
<b>ENCAD</b>	***	***

## Applications and characteristics

- § Dimensionally stable polyester film base which we have modified to provide excellent light stopping power whilst retaining flexibility.
- § Fast drying images are water resistant. Suitable for dye and pigment inks.
- § For multi panel POP-UP displays and applications requiring light stopping performance.

**Caution: (1)** It has been noted with Hewlett Packard 5000 series machines, using HP dye inks to print mixed colours containing less than 50% magenta, that the magenta fades quickly with light exposure causing a colour shift. Tests have, however, shown this also to be the case with most other synthetic materials. If this is a concern, you must satisfy yourself as to the suitability of this product for your application or switch to pigment-based (HP UV) inks, where light-stability is much better.

## Lamination

'Over-lamination of this product after printing can be satisfactorily achieved, however, we strongly recommend that the user ensures the ink of the printed image is thoroughly dry before over-laminating. Printed areas with high ink loadings, which are not thoroughly dry, may cause de-lamination of the laminate. Where there is any doubt regarding the ink being dry we strongly recommend leaving the printed product to dry for a minimum of 24 hours before over-lamination takes place.'

**Recommended conditions for use:** 10°C - 30°C, 30% - 70% RH  
**for storage:** 10°C - 30°C, 20% - 50% RH

**Material Handling, and Shelf Life:** 18 Months

**NOTICE** The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.