

# Scrim Banner Vinyl F375CSV



## Product Data

**Product type:** Polyester reinforced vinyl for inkjet printing  
**Appearance:** Flexible white film with internal woven scrim  
**Surface finish:** Matt coating

## Physical characteristics:

		Typical Value	Test method
<b>Total Thickness <math>\mu</math></b>		375u	Electronic micrometer
<b>Total Weight (gsm)</b>		400	Internal method
<b>CIE Coordinates</b>	<b>L*</b>	97.4	DCI Spectraflash ( D65 10° UV incl.)
	<b>a*</b>	3.9	
	<b>b*</b>	- 12.1	

## Compatibility:

	Large Format	
	Aqueous Dye Inks	Aqueous Pigment Inks
<b>HP</b>	***	***
<b>CANON</b>	***	***
<b>EPSON</b>	***	***
<b>ENCAD</b>	***	***

\*\*\* = Excellent \* \*= Good \*=Fair

*Caution: Disable cutters to avoid damage to the printer*

## Applications and characteristics

- A water-fast, light and flexible banner with a fine structured surface consisting of a tear-resistant polyester fabric with a vinyl layer.
- Good water-fastness, colour brilliance, resolution and edge definition are achieved with pigmented inks.
- Printability is also excellent with dye based inks, although pigmented inks are recommended for all outdoor applications.
- For optimum results, ink limits of about 240% are recommended
- Indoor and outdoor signage/advertising, pop-up displays etc.
- Can be sewn, welded and grommetted for fixing and used outdoors for up to 3 months (unprotected).
- Extremely high tear resistance. Waterfast matt coating with high ink capacity.
- Banners should not be folded and should be left to dry for a minimum of 12 hours prior to outdoor use.

## Available in 914mm (36 inches) and 1067mm (42 inches)

**Recommended conditions for use:** 10°C - 30°C, 30% - 70% RH

**for storage:** 35°C - 65°C, 10% - 25% RH

Ageing will affect the colour of the vinyl and eventually its ink performance.

**Material Handling, and Shelf Life:** 6 Months

**NOTICE** The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.