

Solvent Polymeric Satin P190SPS



Product Data

Product type: Low cost (polypropylene) alternative to photo based paper

Appearance: White

Surface finish: Satin printable coating one side

Physical characteristics:

		Typical Value	Test method
Total Thickness μ		190	Electronic micrometer
Total Weight (gsm)		140	Internal method
Gloss 60°		36	BYK Gardner 60°
CIE Coordinates	L*	98	DCI Spectraflash (D65 10° UV incl.)
	a*	- 0.5	
	b*	- 0.7	

Compatibility:

Ecosolvent + inks, Roland Soljet, Versacamm, Mutoh Rockhopper II, etc. Solvent inks such as Grenadier. Please make your own assessment though, as solvent inks can vary widely. This is more dependent on ink manufacturer and type than it is on printing machine.

Applications and characteristics

- § Photo reproduction & enlargements
- § Great for Indoor use
- § Point of Sales
- § Signs, Posters, Banners, Murals
- § Tear & scratch resistant

Recommended conditions for use: 10°C - 30°C, 30% - 70% RH

for storage: 5°C - 30°C, 20% - 70% RH

Material Handling, and Shelf Life: 12 Months from date of manufacture

NOTICE The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.

Copyright Sensitisers Group 2005

Kernow Coatings Limited +44(0)1326 373147 e-mail: kc@sensitisers.com