

# Hydroprint Clear Adhesive Film S053HCXF

S053HCXF is a Clear aqueous coated polyester film, with a permanent pressure sensitive adhesive laminated to a matt anti-static polyester release liner. The construction is optimised for dry toner print applications.

## Physical characteristics

Property	Typical Value	Unit	Test Method
Total Thickness	160 +/- 5	μ	Electronic micrometer
Weight	205 +/- 6	g/m <sup>2</sup>	Internal method
Face Film Thickness (no adhesive)	53 +/- 2	μ	Electronic micrometer
Liner Thickness	90 +/- 4	μ	Electronic micrometer
Tensile Strength (Face)	MD 14 TD 17	KgF/mm <sup>2</sup>	ASTM D882-83
Melting Point	250	C	ASTM E794-85
Adhesive Peel on Stainless Steel	>12	N/25mm	FINAT 1 (30min dwell)
Adhesive Application Temperature	+5 to +50	C	Internal Method
Adhesive Service Temperature	+0 to +50	C	Internal Method

## Compatibility:

Suitable for most dry toner (laser/LED) & thermal transfer print processes, both mono and colour small-volume, mid-volume & production machines.

On such machines the user must establish for themselves the optimum settings and paper path, being aware of the thickness and weight of the material.

## Applications and characteristics:

- Tear resistant, high stability, water resistant front face.
- For glass clear 'no-label' effect
- Clear / Gloss surface promotes toner adhesion and smoothest imaging on a wide range of toner based printers.
- High grab, high-tack permanent acrylic pressure sensitive adhesive for long duration.
- Film release for optimal lay-flatness & dimensional stability.

**Recommended conditions for use:** 10°C - 30°C, 40% - 55% RH  
**for storage:** 10°C - 20°C, 20% - 55% RH

Please return unused product to its original packaging

## Shelf Life:

18 months after delivery (under recommended storage conditions)

Rev: EU 11/07

**NOTICE** The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.

Copyright Sensitizers Group 2011